

# COOL COLORS PALETTE BY



With ENERGY STAR® Compliant Fluoropon® SR Coatings by



S  
T  
A  
N  
D  
A  
R  
D

## SOLID FLUROPON® PVDF COLORS - KYNAR 500®



REGAL WHITE SR:0.70 E:0.86



ASCOT WHITE SR:0.69 E:0.85




BONE WHITE SR:0.69 E:0.84




SANDSTONE SR:0.61 E:0.85



DOVE GRAY SR:0.47 E:0.86



ZINC GRAY SR:0.35 E:0.86



OLD TOWN GRAY SR:0.41 E:0.85



SURREY BEIGE SR:0.48 E:0.86



RAWHIDE SR:0.55 E:0.85



PARCHMENT SR:0.53 E:0.85



ANTIQU BRONZE SR:0.43 E:0.86



SPARTAN BRONZE SR:0.31 E:0.85



DARK BRONZE SR:0.27 E:0.85



REDWOOD SR:0.38 E:0.86



COLONIAL RED SR:0.32 E:0.86



PATINA GREEN SR:0.41 E:0.84



EVERGREEN SR:0.26 E:0.85



SLATE BLUE SR:0.28 E:0.85



REGAL BLUE SR:0.26 E:0.85



TAHOE BLUE SR:0.26 E:0.85

P  
R  
E  
M  
I  
U  
M

## MICA FLUROPON CLASSIC® II PVDF COLORS



SILVERSMITH SR:0.52 E:0.81



CHAMPAGNE BRONZE SR:0.43 E:0.81



WEATHERED ZINC SR:0.25 E:0.83



COPPER PENNY SR:0.45 E:0.85

## METALLIC FLUROPON CLASSIC® PVDF COLORS



MEDIUM GRAY SR:0.32 E:0.87



LIGHT BRONZE SR:0.49 E:0.85



CHAMPAGNE GOLD SR:0.36 E:0.86



BRIGHT SILVER SR:0.55 E:0.85

S  
T  
O  
C  
K

## IN-STOCK DYNAPON® COLORS - MODIFIED POLYESTER



USDA IMPERIAL WHITE (30 gloss)  
SR:0.62 E:0.86



SANDSTONE SR:0.52 E:0.85



SURREY BEIGE SR:0.44 E:0.86

SR - Solar Reflectivity E - Emissivity  
CRRC rated products are available upon request.



T: 877-METECNO  
www.metecnoinc.com

